

Moplen EP300K

Polypropylene, Impact Copolymer

Product Description

"Moplen" EP300K is a low fluidity heterophasic copolymer, suitable for injection moulding applications. The product exhibits very high impact even at low temperature combined with a good stiffness.

"Moplen" EP300K is typically used in houseware items and in crates.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	Europe, Africa-Middle East
Processing Method	Injection Moulding, Thermoforming
Typical Customer Applications	Crates, Injection Moulded Caps and Closures, Housewares

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.9	g/cm ³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	4	g/10 min
Melt volume flow rate (230°C/2.16Kg)	ISO 1133	5.4	cm ³ /10min
Mechanical			
Tensile Modulus	ISO 527-1, -2	1200	MPa
Tensile Stress at Yield	ISO 527-1, -2	27	MPa
Tensile Strain at Break	ISO 527-1, -2	>50	%
Tensile Strain at Yield	ISO 527-1, -2	7	%
Impact			
Charpy unnotched impact strength (23 °C, Type 1, Edgewise)	ISO 179	No Break	kJ/m ²
(0 °C, Type 1, Edgewise)		140	
(-20 °C, Type 1, Edgewise)		80.0	
Charpy notched impact strength (23 °C, Type 1, Edgewise, Notch A)	ISO 179	10.5	kJ/m ²
(0 °C, Type 1, Edgewise, Notch A)		5.50	
(-20 °C, Type 1, Edgewise, Notch A)		4	
Hardness			
Ball indentation hardness (H 358/30)	ISO 2039-1	53	MPa
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	75	°C
Vicat softening temperature (A50 (50°C/h 10N))	ISO 306	150	°C
(B50 (50°C/h 50N))		71	

Notes

Typical properties; not to be construed as specifications.

© 2003 Basell Service Company B.V.

Before using a Basell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the Basell product safely and legally. (Material Safety Data Sheets are available from Basell at www.basell.com.) This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. No one is authorized to make such warranties or assume any liabilities on behalf of Basell except in a writing signed by an authorized Basell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at Basell's option, and in no event shall Basell be liable for special, consequential, incidental, punitive, or exemplary damages.

Adflex, Adstif, Adsyl, Clyrell, Hifax, Hostacom, Hostalen, Lucalen, Luflexen, Lupolen, Lupolex, Metocene, Moplen, Pro-fax, Pro-fax Ultra, Purell, Spherilen and Valtec are trademarks owned or used by Basell. *Adflex, Adstif, Adsyl, Lucalen, Luflexen, Lupolen, Moplen and Pro-fax* are